

3079

1. BASIC PROPERTIES

Composition

Methyl ethyl ketone	5-10%
Acetone	5-8%
Methyl acetate	20-30%
Ethyl acetate	20-25%
Dimethyl carbonate	30-35%
Polyurethane Resin	13-16%

Appearance: Transparent viscous liquid

Solid content: 13.5-15%

Viscosity (25°C) : 1500-2000 cps

Shelf life: 12 months

2. APPLICATIONS


3079 is a toluene-free anti-yellowing adhesive for shoes making.

3. PROPERTIES

Light color which makes it less conspicuous when applied. Also less discoloring with time pass.

Shows good initial strength and has good repulsive force..

4. APPLICATION PROCESS



Add 3-5% of hardener and stir it to make it even before use.

Mixed cement should be used up within 2 hours.

The above condition is for reference only. The actual conditions should be set and adjusted according to the actual production facilities.

5. PRECAUTIONS

Highly flammable liquid. No open flames.

Close the container air tight after use.

Store at dry and cool place with good ventilation. Make sure the temperature is between 5-40°C.

Please refer to MSDS for more details.

6. PACKING

Tin: 15 kg/tin.