

### 3094

#### 1. 基本物性 BASIC PROPERTIES

主要成分 Composition

丁酮 Methyl ethyl ketone	25-30%
乙酸乙酯 Ethyl acetate	40-50%
甲苯 Toluene	15-20%
合成树脂 Synthetic Resin	8-12%

外观: 淡黄色液体

Appearance: Light yellow liquid

固成份 Solid content: 8-12 %

保存期限: 6 个月

Shelf life: 6 months

#### 2. 用途 APPLICATIONS

3094 为为 TPR 处理剂。


3094 is a primer for TPR.

#### 3. 特性 PROPERTIES

对大多数 TPR 材质有好的接着效果, 气味温和。

Good treatment effect for most TPR with mild odor.

#### 4. 流程 APPLICATION PROCESS



清洁鞋材表面, 必要时请处理鞋底, 干燥后刷胶。

Clean surface and/or apply primer to upper and sole if necessary. Apply adhesive.

干燥时间: 55-65°C × 3-5 分钟, 压合。

Drying time: 55-65°C × 3-5 min. Press.

以上操作条件仅供参考, 应视生产线实际条件而调整。

The above condition is for reference only. The actual conditions should be set and adjusted according to the actual production facilities.

### 5. 注意事项 PRECAUTIONS

易燃液体。禁止明火。

Highly flammable liquid. No open flames.

使用后盖紧容器。

Close the container air tight after use.

储存于阴凉干爽的地方 (5-40°C)。

Store at dry and cool place with good ventilation. Make sure the temperature is between 5-40°C.

详细资料请参考 MSDS。

Please refer to MSDS for more details.

### 6. 包装规格 PACKING

铁桶: 15 公斤/桶。

Tin: 15 kg/tin.