

3098

1. 基本物性 BASIC PROPERTIES

主要成分 Composition

丁酮 Methyl ethyl ketone	15-20%
丙酮 Acetone	18-20%
乙酸乙酯 Ethyl acetate	40-50%
聚氨酯树脂 Polyurethane Resin	20-25%

外观: 淡黄色液体

Appearance: Little yellow liquid

固成份 Solid content: 18-23 %

粘度 Viscosity (25°C) : 300-600 cps

保存期限: 6 个月

Shelf life: 6 months

2. 用途 APPLICATIONS

3098 为油皮处理剂。

3098 is an oil leather primer.

3. 特性 PROPERTIES

无甲苯、无酚。

Free of Toluene and Phenol.

抗油性佳, 防止接着力下降。

Good protect against oil transfer, and prevent adhesion down.

4. 流程 APPLICATION PROCESS



使用时需要添加 5-10%的硬化剂 RFE，并搅拌均匀（5-8 分钟），使用毛刷或棉布沾本剂涂布鞋材表面。

Add 5-10% RFE and stir it for 5-8 min to make it even before use. Apply the primer by brush or cotton cloth.

配合使用 PU 胶。

Use with PU adhesive.

以上操作条件仅供参考，应视生产线实际条件而调整。

The above condition is for reference only. The actual conditions should be set and adjusted according to the actual production facilities.

5. 注意事项 PRECAUTIONS

使用前，检测处理剂对鞋材表面的处理和接着性能。

Before production, check the priming performance of the primer first.

易燃液体，远离火源与热源。

Flammable liquid, avoid flame or heat.

保证工作场所的通风良好。

Ensure good ventilation in the working place.

储存于阴凉干爽的地方（5-40°C）。

Store at dry and cool place with good ventilation. Make sure the temperature is between 5-40°C.

详细资料请参考 MSDS。

Please refer to MSDS for more details.

6. 包装规格 PACKING

铁桶：15 公斤/桶。

Tin: 15 kg/tin.