

3107

1. 基本物性 BASIC PROPERTIES

主要成分 Composition

| | |
|----------------------|--------|
| 乙酸乙酯 Ethyl acetate | 75-85% |
| 聚异氰酸盐 Polyisocyanate | 15-25% |

外观: 无色透明液体

Appearance: Colorless transparent liquid

固成份 Solid content: 15-30 %

保存期限: 6 个月

Shelf life: 6 months

2. 用途 APPLICATIONS

3107 为配合 PU 胶所使用的硬化剂, 用于制鞋行业。

3107 is a hardener for PU adhesive, use for shoes making.

3. 特性 PROPERTIES


耐黄变效果好, 结晶速度适中。

Good yellowing resistance and moderate crosslinking speed.

提高 PU 胶的耐热、耐水解等性能。

Improves resistance of the bonding to: Temperature、Water etc.

4. 流程 APPLICATION PROCESS



使用时需要添加 3-5% 的 3017 到 3081 中, 并搅拌均匀。

Add 3-5% of hardener and stir it to make it even before use.

添加硬化剂后，建议在 2 小时内使用完。

Mixed cement should be used up within 2 hours.

以上操作条件仅供参考，应视生产线实际条件而调整。

The above condition is for reference only. The actual conditions should be set and adjusted according to the actual production facilities.

5. 注意事项 PRECAUTIONS

易燃液体。禁止明火。

Highly flammable liquid. No open flames.

使用后盖紧容器，以免与水汽反应失效。

Close the container air tight after use. Avoid reaction with moisture.

储存于阴凉干爽的地方 (5-40°C)。

Store at dry and cool place with good ventilation. Make sure the temperature is between 5-40°C.

详细资料请参考 MSDS。

Please refer to MSDS for more details.

6. 包装规格 PACKING

铁桶：15 公斤/桶。

Tin: 15 kg/tin.